
Preparation of a Polymeric Foam: An Activity Designed to Increase Teachers' Awareness of the Utility of Condensation Polymerisation

John Cullen¹ and Fraser J. Scott^{2*}

¹WestCHEM Department of Pure and Applied Chemistry, University of Strathclyde, 295 Cathedral Street, Glasgow G1 1XL, UK

²Department of Biological Sciences, School of Applied Sciences, University of Huddersfield, Queensgate, Huddersfield, HD1 3DH, UK

ABSTRACT

The new Scottish 'Curriculum for Excellence' places a greater emphasis on the societal implications of Chemistry concepts, including polymer chemistry. This has led to many Scottish secondary school teachers having little experience and background knowledge with which to satisfactorily explore the topic of polymers as they deliver the curriculum. Here we detail our development of a practical demonstration of polymer foams and its inclusion in a continuous professional development module for Scottish secondary school teachers. This demonstration has now been incorporated into chemistry classrooms across Scotland as a means of exemplifying the topic of polymers.

GRAPHICAL ABSTRACT



KEYWORDS

High School/Introductory Chemistry, Graduate Education/Research, Hands-On Learning/Manipulatives, Polymer Chemistry, Demonstrations

INTRODUCTION

Presently, in Scotland, High School educators are adapting their teaching practices to changes brought about by the introduction of the new Curriculum for Excellence (CfE). This curriculum is focused on developing learners that are prepared to enter society, and more importantly to be able to contribute effectively to it, by helping them to become successful learners, confident individuals, responsible citizens and effective contributors; these are called the four capacities.¹ These new foci necessitate a change in the specific curricular areas that are delivered in secondary science education and is neatly exemplified by both the National 5 and Higher Chemistry curricula having one of three units now entitled ‘Chemistry in Society’.² These units deal with various areas of applied chemistry and the main emphasis is on the applications of chemistry, and how it can affect society (both positively and negatively). This change in focus towards the application of science in society is also reflected in one of the core ideas within the Next Generation Science Standards (NGSS), “The Influence of Engineering, Technology, and Science on Society and the Natural World”.³ Although the theory behind polymer chemistry was a key feature of the previous Scottish curricula, details about its application and importance to society were limited in importance. This has led to many Scottish secondary school teachers having little experience and background knowledge with which to satisfactorily explore the topic of polymers as they deliver the curriculum. This is also true in the US system, with the introduction of the NGSS.

The Department of Pure and Applied Chemistry at the University of Strathclyde has recently responded to significant requests for greater Continuous Professional Development (CPD) opportunities from secondary school teachers across Scotland by


1
2
3
4
5 developing a suite of CPD modules. These modules were designed to provide the
6
7 50 teachers with up to date information and practical exemplification of parts of the new
8
9 chemistry curricula that did not feature heavily, or at all, in the previous Scottish
10
11 curricula, including the topic of polymers. We are pleased to see that recently a number
12
13 of US-based counterparts are too developing polymer-based modules, aimed at
14
15 generating positive impact at the secondary school level.^{4,5} This demonstration presents
16
17 55 an experiment that we developed to provide practical exemplification of the uses of
18
19 polymers in society, specifically that of polymeric foams. We incorporated this
20
21 experiment within our CPD module entitled, “Linking Theoretical and Practical Aspects
22
23 in the National 5 Curriculum”, with the aim that it would be subsequently incorporated
24
25 into the participating teachers’ teaching practices, and thus have wide spread reach
26
27 60 throughout Scotland.

28 29 **Polymeric foams**

30 Polymeric foams are materials that are prepared by gas molecules becoming trapped
31
32 in a solid polymer matrix. Polymeric foams are encountered routinely in daily life.
33
34 Typical applications of polymeric foams include packaging materials, upholstery and
35
36 65 insulation. Polymeric foams can be prepared from a number of chemistries and
37
38 methods, but most common types routinely used include polyurethanes and
39
40 polystyrene.⁶ However, the preparation of polyurethane and polystyrene foams in a
41
42 classroom environment, although not impossible,⁷ does offer some practical challenges
43
44 associated with exposure to toxic reactants, such as isocyanates.

45 70 There are other chemistries that are more appropriate for active experimentation by
46
47 science pupils. One such chemistry type is urea-formaldehyde (UF),⁶ which is routinely
48
49 applied in the wood bonding industry for preparing wood panel boards.⁸ UF polymeric
50
51 foams have also been used as insulation in residential dwellings.⁹ Under specific
52
53 conditions and using specialist equipment it is possible to prepare UF polymeric foams.
54
55
56
57

75 UF foams are prepared using two main materials; urea and formaldehyde. The
 76 resulting reaction products are varied with respect to their structure and functionality.
 77 The urea-formaldehyde reaction occurs in two steps. The first step involves
 78 methylation of urea under alkaline conditions. The degree of methylation can be
 79 controlled to some extent in the ratio of urea to formaldehyde. The second step involves
 80 a polycondensation between the methylols to afford linear and branched polymers
 (scheme 1). In industrial applications the reaction between urea and formaldehyde is
 facilitated by the use of specialist machinery.¹⁰ To convert the liquid urea and
 formaldehyde precursors into foams the machinery uses compressed air and a mixing
 nozzle. As the urea and formaldehyde react to form a solid the air is trapped and foam
 85 is produced.



Scheme 1: The preparation of substituted methylol ureas and their subsequent polymerization.

75 In the context of a practical demonstration in a classroom, the use of complicated
 76 machinery to form urea-formaldehyde foam is unfeasible. The experiment described
 77 here does not require any specialist equipment to prepare UF foam. Addition of a dilute
 78 acid to a UF solution containing sodium bicarbonate generates carbon dioxide gas,
 79 while also initiating the polycondensation of the methylolated urea. The experiment can
 80

1
2
3
4
5 be altered at a number of stages to highlight important aspects of chemistry and
6 polymer chemistry such as viscosity, acid reactant (type and concentration), and the
7
8 effect of surfactants/additives.
9

10 11 **EXPERIMENT**

12 **Description of Experimental Apparatus**

13
14 Standard laboratory glassware and apparatus are required for running the
15
16 experiment: glass or plastic bottle as reaction vessel; magnetic stirrer bar and magnetic
17
18 hot plate; solution of phosphoric acid and urea-formaldehyde (Aerolite 306); and, a
100
19 surfactant (figure 1). The various components can be pre-weighed and stored prior to
20
21 use by the teacher or technician.
22
23



35
36 **Figure 1: Equipment and materials required for the preparation of UF foam.**

37 **Experimental – General Preparation of UF foam**

38
39 To a suitable flask was added water (10 mL) and a magnetic stirrer bar. The
40
41 flask was placed on a magnetic stirrer hotplate and to it was added Aerolite 306 (10 g)
42
43 in small portions and mixed until homogeneous. To the Aerolite 306 solution was added
44
45 sodium bicarbonate (0.5 g) and mixed until homogeneous. In a separate beaker was
110
46 added 16% phosphoric acid solution (10 mL). To the beaker containing the phosphoric
47
48 acid was added the surfactant, Tween 80 (0.3 g). The surfactant should be mixed with a
49
50 glass rod to ensure good mixing with the phosphoric acid solution.
51
52
53
54
55
56
57

1
2
3
4
5 To the Aerolite 306 solution was rapidly added the beaker of phosphoric acid
6 solution and surfactant. The magnetic stirrer can be switched off after 15-30 seconds,
7
8
9 115 upon formation of the polymer foam.

10
11 Tips for a successful experiment – The various chemicals and solutions used can
12 be pre-weighed prior to being provided to the participants. The pre-weighing is
13 especially helpful when there are a large number of participants and the availability of
14 balances is limited. The Aerolite 306 may agglomerate if added too quickly to the water,
15
16
17
18 120 if this is the case the clumps should be broken up with a spatula/glass rod to allow for
19 a homogeneous solution of urea-formaldehyde to be prepared. Before the foam begins to
20 react and harden the magnetic stirrer used to mix the reactants can be extracted
21 quickly by use of a magnetic retriever. The foam reaction vessel should be placed on top
22 of some paper towels, to facilitate a simple clean up, in cases where the foam reaction
23
24
25
26
27
28 125 escapes the reaction vessel (figure 2).



30
31
32
33
34
35
36
37
38
39
40
41
42 **Figure 2: A paper towel used to facilitate clean up.**

43
44 The experimental procedure sheet can be found as supporting information.

45 **Experimental – Variations on Foam Preparation**

46
47 130 It is possible to alter the standard experimental to investigate ancillary areas
48 associated with polymer chemistry.

49
50
51 *Viscosity* - the concept of viscosity can be explained by investigation of various
52 concentrations of Aerolite 306. At concentrations greater than 50 % (w/v) the solution
53 will become difficult to stir by use of a magnetic stirrer. It is also possible to decrease
54
55
56

1
2
3
4
5 135 the concentration of Aerolite 306 to show that it is possible to decrease the viscosity of
6
7 the system, but at the expense of the volume and quality of foam prepared.

8
9 *Acid reactant* - Phosphoric acid (16 %) is used in the standard experimental. It is
10 possible to use alternative concentrations to show what effect this has on the rate of
11 reaction and the quantity and quality of foam produced. It is also possible to investigate
12
13
14 140 other acidic solutions, such as formic acid, and observe their effects on the urea-
15 formaldehyde reaction.
16

17
18 *Surfactants and additives* – The omission of either the sodium bicarbonate or the
19 surfactant will have significant effects on the outcome of the reaction. Failure to add the
20 sodium bicarbonate will provide a solid material as opposed to foam. It is also possible
21
22
23
24 145 to vary the concentration of sodium bicarbonate used to obtain foam with varied
25 density. If the sodium bicarbonate is added, but the surfactant is omitted, the cells of
26 the foam will not be stabilized, whilst the reaction between urea and formaldehyde
27 proceeds to completion. Different surfactants, other than Tween 80, could also be
28 investigated.
29
30
31
32
33

34 150 **Hazards and hazard mitigation**

35 The UF used during the experiment is purchased in powder form. The powder UF is
36 converted to a solution and used as such during the activity. UF may contain residual
37 formaldehyde. To mitigate any potential risk of exposure to formaldehyde the UF should
38 be pre-weighed in a fume cupboard and bottled prior to use by the activity participants.
39
40
41
42

43 155 The phosphoric acid is corrosive and an irritant. The dilute solution should be
44 prepared by the activity coordinator and given to the activity participants pre-weighed
45 so as to prevent exposure.
46
47
48

49 Given the hazards associated with UF and phosphoric acid the participants are
50 required to wear safety glasses and gloves during the activity.
51
52
53
54
55
56
57

1
2
3
4
5 160 The reaction generates carbon dioxide when the phosphoric acid is added to the
6 urea-formaldehyde solution. The reaction vessel should not be capped as the gas is
7 generated, as this capping may result in pressurization of the reaction vessel. The
8 reaction vessel should be left to stand uncapped for a minimum of 24 hours before
9 capping to ensure the risk of pressurization is minimized.
10
11
12
13
14

15 165 **RESULTS AND DISCUSSION**

16 Experiment Implementation

17 The experiment can be completed in 10-15 minutes if using only one set of
18 conditions. During the running of the CPD module, we had teachers working in pairs to
19 simulate the experience that we intended to be given to students who would eventually
20 carry out the experiment.
21
22
23 170 carry out the experiment.
24

25 The variations to the experimental (viscosity, acid reactant and the presence of
26 additives) of the foam experiment allow for investigation into other areas of scientific
27 interest beyond polymerisation.
28
29
30

31 The viscosity and concentration of the UF solution has significant effects on the
32 quality of foam produced. Students will find that concentrated solutions of UF will be
33 175 difficult to disperse and will not be suitable to be converted to foam. If the students
34 make the UF solution dilute they will recognize the low viscosity, but at the expense of
35 the foam quantity and quality produced.
36
37
38
39
40

41 Moving from phosphoric acid to formic acid solution (30-60 %) will result in a much
42 reduced rate of foam reaction. The absence of key components such as the surfactant
43 180 or sodium bicarbonate will affect the generation and stabilization of the foam. For
44 example, the importance of sodium bicarbonate can be demonstrated by comparing the
45 density of the foam prepared with sodium bicarbonate (top, figure 3) against material
46 prepared without sodium bicarbonate by placing both in a beaker of water (bottom,
47 figure 3).
48
49
50
51
52
53 185 figure 3).
54
55
56
57




Figure 3: Comparing the density of foam prepared with sodium bicarbonate (top) against material prepared without sodium bicarbonate (bottom) by placing in a beaker of water.

Developing Polymer Knowledge in Secondary Teachers and Students

190 This experiment was carried out by 30 secondary school teachers during a CPD module
23 run in 2016, and by a further 16 teachers in a repeat presentation of the module in
24 2017. We asked the teachers to assess the usefulness of this practical through
25 completion of a short questionnaire comprised of a 5-point Likert-like response item (of
26 no use; of very little use; of some use; useful; very useful) and the opportunity to
27 provide free text response. 93% (43 out of 46) of the teachers responded that they found
28 the experiment either useful or very useful, with 87% (40 out of 46) responding that
29 they found the experiment to be very useful. Further encouraging comments were seen
30 in the free text responses where the most frequent comments related to the teachers'
31 desires to carry out the experiment in the classes e.g. "I'm excited to try this out with
32 my class when we get to the polymers topic". Although this experiment was delivered to
33 teachers during one of our CPD modules, we did this in the hope that they would
34 incorporate it into their delivery of the curriculum in their classrooms. Our ultimate
35 goal was to enrich the experience school students have of the polymer curricular area.
36 Thus, rather than measuring the success of the experiment through gauging teachers
37 perceived usefulness of the experiment, we believe that a better measure of success can
38 be determined through measuring the number of students that have experienced this
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

activity as a result of our training of their classroom teachers. To this end, we surveyed all participants of the CPD modules 3 months after their delivery and, pleasingly, our feedback has indicated that at least 1000 secondary school students across Scotland have now carried out this experiment.

ASSOCIATED CONTENT

Supporting Information

The experimental procedure sheet used during the CPD module, and that to be used in classes with students. A risk assessment sheet for the experiment.

AUTHOR INFORMATION

Corresponding Author

*E-mail: fraser.j.scott@strath.ac.uk

ACKNOWLEDGMENTS

The authors would like to thank Debbie Willison, Lyndsay McCulloch and Margaret Wilson for their support during the running of the experiment during the CPD module.

REFERENCES

- 1 Education Scotland, Building the Curriculum 1: The Contribution of Curricular Areas, [https://education.gov.scot/scottish-education-system/policy-for-scottish-education/policy-drivers/cfe-\(building-from-the-statement-appendix-incl-btc1-5\)/Building%20the%20Curriculum](https://education.gov.scot/scottish-education-system/policy-for-scottish-education/policy-drivers/cfe-(building-from-the-statement-appendix-incl-btc1-5)/Building%20the%20Curriculum), accessed Dec 2017.
- 2 Education Scotland, Experiences and Outcomes, [https://education.gov.scot/scottish-education-system/policy-for-scottish-education/policy-drivers/cfe-\(building-from-the-statement-appendix-incl-btc1-5\)/Experiences%20and%20outcomes](https://education.gov.scot/scottish-education-system/policy-for-scottish-education/policy-drivers/cfe-(building-from-the-statement-appendix-incl-btc1-5)/Experiences%20and%20outcomes), accessed Dec 2017.
- 3 NGSS Lead States. Next Generation Science Standards: For States, By States; The National Academies Press: Washington, DC, 2013.
- 4 Cersonsky, R. K., Foster, L. L., Ahn, T., Hall, R. J., van der Laan, H.L., and Scott, T. F., Augmenting Primary and Secondary Education with Polymer Science and Engineering, *J. Chem. Educ.* 2017, 94 (11), 1639–1646; DOI: 10.1021/acs.jchemed.6b00805.
- 5 Ting, J. M., Ricarte, R. G., Schneiderman, D. K., Saba, S. A., Jiang, Y, Hillmyer, M. A., Bates, F. S., Reineke, T. M., Macosko, C. W., and Lodge, T. P., Polymer Day: Outreach Experiments for High School Students, *J. Chem. Educ.* 2017, 94 (11), 1629–1638; DOI: 10.1021/acs.jchemed.6b00767.
- 6 Suh, K. W. Foamed Plastics. In Kirk-Othmer Encyclopedia of Chemical Technology; John Wiley & Sons: Hoboken, NJ, 2000; DOI: 10.1002/0471238961.06150113192108.a01.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

-
- 7 Pinto, M. L., Formulation, Preparation, and Characterization of Polyurethane Foams, *J. Chem. Educ.*, 2010, **87**, 212–215.
- 245 8 Dunky, M., Urea–formaldehyde (UF) adhesive resins for wood, *Int. J. Adhes. Adhes.*, 1998, **18**, 95–107.
- 9 Schutz, C. A., Urea Formaldehyde Foam for Insulation, *J. Cell. Plast.*, 1968, 37–40.
- 250 10 Heath, R. Aldehyde Polymers: Phenolics and Aminoplastics. In *Brydson's Plastics Materials*; Butterworth-Heinemann: Oxford, UK, 2017; pp 705–742.